



#32-984 / #32-985 Boss Gloss™ Cure & Seal Clear Enhancer- Low VOC

DESCRIPTION

BOSS GLOSS™ CURE & SEAL CLEAR ENHANCER is a Low VOC, styrene-acrylic copolymer solution formulated to achieve both a protective and decorative finish as well as allow the concrete to attain full mix design properties. BOSS GLOSS™ CURE & SEAL CLEAR ENHANCER is a film-forming sealer, which will assist the curing of freshly placed concrete. BOSS GLOSS™ CURE & SEAL CLEAR ENHANCER is formulated as follows:

Slow drying, High solids (25%) formulation for sprayability. Two coats of BOSS GLOSS™ CURE & SEAL CLEAR ENHANCER are preferred to one thick coat. A better Low VOC formulation than the competition!

FEATURES

- * High Gloss
- * Wet Look
- * High Solids
- * U.V. Resistant
- * Slower Drying
- * Easy to Spray

PREPARATION

Clean dirt, wax, grease, oil and other contaminants from the surface. Be sure to remove any foreign coating unless previous coating is same or similar solvent-based sealer. Make sure the surface is clean, dry and sound. Clean oily concrete with a cleaner degreaser. Use a bristle brush for heavily oiled spots. Rinse well with a pressure washer. Allow 24 hours to dry. Apply only when surface and air temperatures are above 50° F and below 90° F. Do not apply to excessively hot surfaces as rapid drying may cause bubbles to form. For pavers, sweep away any loose sand.

APPLICATION

When applying to fresh concrete, wait until all bleed water has evaporated. For best results apply BOSS GLOSS™ CURE & SEAL CLEAR ENHANCER with a solvent-resistant sprayer. Hold conical spray tip no more than 8" from surface. If product must be rolled be sure to use a solvent-resistant non-shedding roller cover. Use a long nap roller for exposed aggregate, a medium nap roller for textured surfaces and a short nap roller for smooth surfaces. Keep roller soaked by dipping on every stroke. Every few feet turn perpendicular to the first coat, and cross roll without re-dipping. Wait until the surface is tack-free before applying a second coat.

The continual dipping with the first coat gives a heavy application and the cross-rolling allows for an even application. Clean up immediately with aromatic solvent such as Xylene. Do not thin product. Foot traffic should be avoided for 4 hours. Vehicle traffic should be avoided for 48-72 hours. Cooler temperatures or increased humidity will slow the dry.

NET COVERAGE RATE: Two thin coats are recommended.

Smooth Troweled: 300 ft² per gallon

Textured or Stamped: 200 ft² per gallon

Uncured Broom Swept: 200 ft² per gallon

Exposed Aggregate and Pavers: 100 ft² per gallon

TECHNICAL DATA

VOC: <350 g/L

Flash Point: 40° F

HMIS

Health 2

Reactivity 0

Flammability 3

Protection B

BOSS GLOSS™ CURE & SEAL CLEAR ENHANCER Meets or Exceeds: ASTM C-309, Type I Class A & B; ASTM C-1315; AASHTO Spec M-148; EPA 40 CFR Part D

SLIP RESISTANCE

For additional slip resistance, apply one coat of BOSS GLOSS™ CURE & SEAL CLEAR ENHANCER. Mix GATOR GRIP™ SLIP RESISTANT ADDITIVE into sealer and apply with second coat.

CLEANUP

Clean tools with Xylene immediately after use.

MAINTENANCE

Clean sealed surface with water only. Reseal surface no more than two years or as needed to prevent buildup of sealer.

DISCLAIMER: Since manufacturer has no control over handling, use or storage; no guarantee expressed or implied, is offered. The suitability of the product for use shall be solely up to the user. Manufacturer retains the right to venue.